



DCI Concrete Pigment Gray-based Color Chart

Maize 600 - 1 lb.	Aztec Gold 600 - 2 lb.	Macadamia 550 - 1 lb.	Beige 650 - 1 lb.	Ramie 609 - 1 lb.	Battleship Grey 230 - 2 lb.
Brick Red 1835 - 4 lb.	Sundried Tomato 1835 - 1 lb.	Merlot 126 - 3 lb.	Evening Shadow 126 - 1 lb.	Terra Cotta Plain 560 - 5 lb.	Majestic Sunrise 1830 - 4 lb.
Dawn 1830 - 1 lb.	Earthen Red 1115 - 3 lb.	Desert Rouge 1115 - 1 lb.	Thyme 300 - 2 lb.	Navajo 543 - 5 lb.	Uplands 543 - 3 lb.
Caramel 543 - 2 lb.	San Juan 543 - 1 lb.	Frontier Buff 533 - 1 lb.	Burnished Copper 553 - 4 lb.	Sandstone 553 - 1 lb.	Canyon Brown 533 - 5 lb.
Santa Fe Tan 533 - 3 lb.	Smokestack 230 - 5 lb.	Weathered Tin 230 - 1 lb.	Deep Bronze 680 - 3 lb.	Milk Chocolate 680 - 1 lb.	Rattan 609 - 4 lb.
Golden Buff 609 - 2 lb.	Cocoa Brown 653 - 3 lb.	Walnut 649 - 4 lb.	Petrified Wood 649 - 2 lb.	Reed Grass 300 - 1 lb.	Briar Buff 500 - 3 lb.
Taupe 653 - 1 lb.	Cafe Au Lait 649 - 1 lb.	Sage 1198 - 2 lb.	Rocky Crag 623 - 3 lb.	Wildwood Buff 500 - 2 lb.	Wheat Buff 500 - 1 lb.
Wool Tweed 1198 - 4 lb.	Winterfield Buff 1198 - 1 lb.	Mocha 623 - 1 lb.	Tarnished Brass 1311 - 3 lb.	Sunray 1311 - 1 lb.	Olive Tree 300 - 3 lb.
Sand 500 - 1.5 lb.	Umber 1880 - 3 lb.	Barely Lavender 1880 - 1 lb.	Heather 500 - 0.5 lb.	Tumbleweed 650 - 2 lb.	Bamboo 550 - 2 lb.

Direct Colors pigments are lightfast, odorless, alkali and weather resistant, UV stable, non-hazardous, chemically inert, water soluble and tested to ASTM C979. We have commercial, residential and sample size quantities available for projects large and small. Color matching provided for larger projects. All color chips have been sealed with a solvent based sealer. Color will vary with sealer choice.

Blue Gray

1551 - 0.5 lb.

Ocean Blue

1551 - 1 lb.

Denim

1551 - 2 lb.

Midnight
Blue

1551 - 3 lb.

Pacific
Blue

15.4 - 0.50 lb.

Prairie
Blue

15.4 - 1 lb.

Slate
Blue

75 - 3 lb.

Steel
Blue

75 - 5 lb.

Sea
Green

5376 - 2 lb.

Mint
Green

5376 - 3 lb.

Forest
Green

5376 - 5 lb.

Ash

Ti02 - 5 lb.



Several online concrete pigment calculators are available at DirectColors.com to help customers calculate pigment quantities. The pigment needed to achieve a specific color is based on the amount of cement in the mix rather than the total concrete weight. The project calculator tool is designed to calculate for truck pours, custom concrete batches, such as stucco, mortar or grout, 5000 psi countertop mixes and bags of ready mix concrete.



INTEGRAL COLOR DISCLAIMER: Because the conditions of use and application of our products are beyond the manufacturer's control, Direct Colors makes no warranty regarding workmanship and other variables that do not involve the performance of our pigments. Buyer's sole remedy shall be the purchase price paid by the user or buyer for the quantity of the Direct Colors product involved. All colors represented on these color charts are actual photographs of integrally colored concrete samples using Direct Colors pigments. Differences in type and even brand of cement can and will influence the final color appearance. For best results, conduct a sample pour using the exact components involved in the actual pour.

The Possibilities are *Endless* with Concrete Pigment!

3000 PSI

- 0.5 lb mix = 2.5 lbs pigment per yard
- 1 lb mix = 5 lbs pigment per yard
- 2 lb mix = 10 lbs pigment per yard
- 3 lb mix = 15 lbs pigment per yard
- 4 lb mix = 20 lbs pigment per yard
- 5 lb mix = 25 lbs pigment per yard

3500 PSI

- 0.5 lb mix = 2.75 lbs pigment per yard
- 1 lb mix = 5.5 lbs pigment per yard
- 2 lb mix = 11 lbs pigment per yard
- 3 lb mix = 16.5 lbs pigment per yard
- 4 lb mix = 22 lbs pigment per yard
- 5 lb mix = 27.5 lbs pigment per yard

4000 PSI

- 0.5 lb mix = 3 lbs pigment per yard
- 1 lb mix = 6 lbs pigment per yard
- 2 lb mix = 12 lbs pigment per yard
- 3 lb mix = 18 lbs pigment per yard
- 4 lb mix = 24 lbs pigment per yard
- 5 lb mix = 30 lbs pigment per yard

4500 PSI

- .05 lb mix = 3.25 lbs pigment per yard
- 1 lb mix = 6.5 lbs pigment per yard
- 2 lb mix = 13 lbs pigment per yard
- 3 lb mix = 19.5 lbs pigment per yard
- 4 lb mix = 26 lbs pigment per yard
- 5 lb mix = 32.5 lbs pigment per yard

(Contact Direct Colors for additional PSI calculations)